

A193-B8 / B8A

DIN		ASTM	A193 B8 / B8A
AISI	304	UNS	S30400
Handelsnaam		SAE	
Alloy		BS	
EN		AFNOR	

Opmerking:

Chemische Samenstelling:

Element	%C	%Mn	%P	%S	%Si	%Cr	%Ni				
min	0	0	0	0	0	18,00	8,00				
max.	0,08	2,00	0,045	0,030	1,00	20,00	11,00				
Element											
min											
max.											

Beschrijving:

Mechanische eigenschappen

Rm min	515 N/mm2
--------	-----------