

**A194-8 / 8A**

DIN		ASTM	A194-8 / 8A
AISI		UNS	S30400
Handelsnaam		SAE	
Alloy		BS	
EN		AFNOR	

**Opmerking:**

**Chemische Samenstelling:**

Element	%C	%Mn	%P	%S	%Si	%Cr	%Ni				
min	0	0	0	0	0	18,0	8,0				
max.	0,08	2,00	0,045	0,030	1,00	20,0	11,0				
Element											
min											
max.											

**Beschrijving:**