

A320-B8C / B8CA

DIN		ASTM	A320-B8C / B8CA
AISI		UNS	S34700
Handelsnaam		SAE	
Alloy		BS	
EN		AFNOR	

Opmerking:

Chemische Samenstelling:

Element	%C	%Mn	%P	%S	%Si	%Ni	%Cr	%Co+%Ta		
min	0	0	0	0	0	9,0	17,0	10x%C		
max.	0,08	2,00	0,045	0,030	1,00	12,0	19,0	1,10		
Element										
min										
max.										

Beschrijving:

Rm min	515 N/mm ²
A	30%