

**Werkstofnummer: 1.6368 mark. 6368**

DIN	15NiCuMoNb5	ASTM	
AISI		UNS	K12039 / K12042 / K12529 / K12539 / K12554 / K12766
Handelsnaam		SAE	
Alloy		BS	
EN		AFNOR	

**Opmerking:**

**Chemische Samenstelling:**

Element	%C	%Si	%Mn	%P	%S	%Cr	%Mo	%Ni	%Nb	%Al	%Cu
min	0	0,25	0,80	0	0	0	0,25	1,00	0,015	0,015	0,50
max.	0,17	0,50	1,20	0,03	0,025	0,30	0,50	1,30	0,045		0,80
Element	%N										
min	0										
max.	0,020										

**Beschrijving:**